



TEST REPORT

LAB NO.: (5919)098-0490
FORM NO.: /
DATE IN: APR. 08, 2019
MODIFIED DATE: /
DATE OUT: APR. 12, 2019
NO. OF WORKING DAYS: 5
PAGE 1 OF 5

OVERALL RATING

PASS _____
FAIL _____
DATA _____ **X**

Vendor:	JIANGYIN SHENFEI KNITTING CO LTD	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	/
Sample Description:	/	Style Description:	/
Color:	/	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	/

Product Category:	/
Test Requested:	/
Previous Report No.:	/

Submitted Fiber Content:	/
Actual Fiber Content:	/
Suggested Fiber Content:	/
Submitted Care Instruction(s):	MACHINE WASH COLD, GENTLE CYCLE, TUMBLE DRY LOW, ONLY NON-CHLORINE BLEACH WHEN NEEDED
Client Expected Care Instruction:	/
Suggested Care Instruction(s):	/

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
COLOURFASTNESS TO WASHING			X	
COLOURFASTNESS TO RUBBING			X	
COLOURFASTNESS TO SALIVA			X	
pH VALUE OF TEXTILES: ISO 3071			X	
PHENOLS CONTENT			X	

Remark: BVCPS (JiangSu) contact information for this report

General Information:

Tony Xu Tel: 0510-86991171, Email: tony-lf.xu@cn.bureauveritas.com

Nancy Zhou Tel: 0510-86938200, Email: fei.zhou@cn.bureauveritas.com

Technical Questions:

Lynn Yu Tel: 0510-86930372, Email: lynn.yu@cn.bureauveritas.com

Ada Yin Tel: 0510-86938211, Email: ada.yin@cn.bureauveritas.com

BUREAU VERITAS

CONSUMER PRODUCTS SERVICES (JIANGSU)



PETER WANG

TECHNICAL MANAGER

<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>	<u>REQUIREMENTS</u>
<u>COLOURFASTNESS TO WASHING</u> (ISO 105-C06:2010, DW, TEST NO: A2S , 30-MIN MECHANICAL WASH AT 40 DEGREE CELSIUS IN 0.4% ECE DETERGENT AND 0.1% SODIUM PERBORATE SOLUTION)		
COLOUR CHANGE	4-5	/
COLOUR STAIN ON		/
ACETATE	4-5	
COTTON	4-5	
NYLON	4-5	
POLYESTER	4-5	
ACRYLIC	4-5	
WOOL	4-5	
<u>COLOURFASTNESS TO RUBBING</u> (ISO 105-X12:2002)		
LENGTH		
DRY	4-5	/
WET	4-5	/
WIDTH		
DRY	4-5	/
WET	4-5	/
<u>COLOURFASTNESS TO ARTIFICIAL SALIVA</u> (DIN 53160-1)		
COLOR STAINING	5	/
<u>pH VALUE OF TEXTILES: ISO 3071</u> (ISO 3071: 2005)		
pH VALUE	6.9	/

<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>	<u>REQUIREMENTS</u>
-----------------------------	----------------------------	----------------------------

Phenols Content

Test Method : §64 LFGB B 82.02-8:2001 (Modified)

Tested Item(s) : 1 BLACK FABRIC

Client's Limit:	/	
Parameter	Unit	Result
-	-	1
PCP	mg/kg	ND
TeCP	mg/kg	ND
Conclusion	-	DATA

Note:

ND = Not detected ">" = More than
mg/kg = milligram per kilogram
Detection Limit (mg/kg): Each 0.05

Remark:

- The name(s) and Chemical Abstracts Service number(s) (CAS-No.) of phenols are shown in tab of Appendix.

Phenols:					
No.	Name	CAS-No.	No.	Name	CAS-No.
1	Pentachlorophenol (PCP)	87-86-5			
2	Tetrachlorophenol (TeCP): 2,3,5,6- Tetrachlorophenol 2,3,4,6- Tetrachlorophenol 2,3,4,5- Tetrachlorophenol	935-95-5 58-90-2 4901-51-3			

COLOURFASTNESS RATING

GRADE 5 NEGLIGIBLE OR NO CHANGE OR STAINING
GRADE 4 SLIGHTLY CHANGED OR STAINED
GRADE 3 NOTICEABLY CHANGED OR STAINED
GRADE 2 CONSIDERABLY CHANGED OR STAINED
GRADE 1 MUCH CHANGED OR STAINED

C/N SM JY/MZ/VH

